



# EXCURE FLEXO UV VARNISHES FOOD

## CHARACTERISTIC

*These UV varnishes are radical UV varnishes, formulated without benzophenone, very low in odour and with low migration properties.*

## PROPERTIES

- ☞ *These varnishes can be applied wet-on-dry on conventional inks and wet-on-wet or wet-on-dry on Excure UV inks*
- ☞ *The surface tension of the cured film is typically < 34 mN/m for non gluable varnishes and ± 38 mN/m for gluable varnishes.*
- ☞ *These varnishes are formulated with very low toxicity ingredients*
- ☞ *Low in wet odour and very low odour in the cured print*
- ☞ *These varnishes have very good clarity*
- ☞ *These varnishes are press ready at optimal viscosity*
- ☞ *These varnishes can be used with normal flexo and letterpress plates*
- ☞ *Optimal resistance properties will be obtained 24 hours after printing*

Article	Viscosity 21°C/DIN 4 mm	Cure	Slip	Gloss	Rub / scuff	Property
EXC90004/E	55 – 80 sec	High	Medium	High	Medium	Standard
EXC99076	50 – 70 sec	Very high	High	High	Medium/High	More reactive
EXC99095	40 – 60 sec	High	High	High / Medium	High	High slip, anti- blocking
EXC97014	50 – 80 sec	High	Low	High	Medium	Gluable, Standard

## TYPES

- *Radical chemistry*

## APPLICATION AREA

- Varnishing machines / coaters*

## SUITABLE SUBSTRATES (min. surface tension 38 dynes/cm)

- ☞ All kinds of paper and board
- ☞ Certain corona treated PE-films
- ☞ Other substrates: to be tested

## REMARKS

- ★ Both EPDM and nitril rubber rollers are suitable when using these varnishes.
- ★ Shelf life: all UV varnishes have a 12-month shelf life guarantee. This guarantee covers 12 months from the date of manufacture (which is mentioned on the label). In order to give this guarantee, certain recommendations must be followed: UV varnishes should be kept on stock at temperatures between 15 – 20°C and they should not be exposed to direct sunlight. If possible, store the varnish in a dark room.
- ★ Stir well before use.

## PACKAGING

- ☐ 10 kg jerry cans
- ☐ 25 kg jerry cans
- ☐ 200 kg barrels
- ☐ 600 kg containers
- ☐ 1000 kg containers

## ADDITIVES

◆ Wash up solution	for manual washing	EXC10810
	for automatic washing	EXC10800
	labelling and reg. free	EXC10820
◆ Photoinitiator		EXC10045
◆ Levelling agent	non gluable	EXC10024
	Gluable	EXC10030
◆ Thinner		EXC10705
◆ Slip agent		EXC10005
◆ Anti penetration additive		EXC10013

## OTHER INFO

*These inks and/or coatings (this ink and/or coating) are (is) only suitable for use on the non-food contact side of food packaging, provided they are applied using the relevant Good Manufacturing Practices (GMP) and according to the guidelines in this Technical Data Sheet. The printer, converter and packer/filler each have a responsibility to ensure that the finished – printed - product is fit for the intended purpose(s) and that the ink and coating components do not migrate into the food at levels that exceed legal, regulatory and industry defined requirements*